ALTECH PP-H A 4925/500 MR25

PP-T25 MOCOM Compounds GmbH & Co. KG

Product Texts	
Base Polymer	Polypropylene Homopolymer
Filler/Additive System	25 % talcum
Market Segment	various,Furniture
Typical Applications	various

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
[C] Melt volume-flow rate, MVR	**25**	cm³/10min	ISO 1133
Temperature	**230**	°C	-
Load	**2.16**	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**3000**	MPa	ISO 527
[C] Yield stress	**32**	MPa	ISO 527
[C] Yield strain	**4.6**	%	ISO 527
[C] Charpy impact strength, +23°C	**40**	kJ/m²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	**3**	kJ/m²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
[C] Temp. of deflection under load, 1.80 MPa	**80**	°C	ISO 75-1/-2
[C] Vicat softening temperature, B	**98**	°C	ISO 306

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Density	**1090**	kg/m³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Features

Homopolymer

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

Pre-Drying Conditions	in a dry air (dessiccant) dryer 60-90 °C for 2-4 h in an air circulating dryer 60-90 °C for 2-4 h
Processing Injection Moulding	melt temperature 200-270 °C mould temperature 20-70 °C
Storage	dry, protected from light not above 30°C

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.