

Hostacom BB 1113 F BLACK

PP-T25

LyondellBasell Industries

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| Melt flow index, MFI | 4 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ISO Data | | | |
| Yield stress | 19 | MPa | ISO 527 |
| Flexural modulus, 23°C | 2000 | MPa | ISO 178 |
| Izod notched impact strength, +23°C | 30 | kJ/m ² | ISO 180/1A |
| Thermal properties | | | |
| ISO Data | | | |
| Temp. of deflection under load, 0.45 MPa | 118 | °C | ISO 75-1/-2 |
| Other properties | | | |
| Density | 1100 | kg/m ³ | ISO 1183 |

Characteristics**Processing**

Injection Molding

Applications

Automotive

Delivery form

Pellets, Black

Regional Availability

Europe

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather