

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	24	MPa	ISO 527
Strain at break	5	%	ISO 527
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Other properties			
Density	1140	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Features

Low Emission, Low Fogging, Low Odor, Copolymer

Applications

Automotive

Regional Availability

Europe