

Green ISOFIL® K 30 T T HS

PP-T30

Sirmax S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Yield stress	23	MPa	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	62	°C	ISO 75-1/-2
Vicat softening temperature, B	68	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Other properties			
Density	1130	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Features

Copolymer

Certifications

RoHS compliant

Applications

Building Construction

Regional Availability

North America, Europe, Asia Pacific, South and Central America