

Hifax TYC 258P 9B9 BLACK

PP-T30

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	20.5	MPa	ISO 527
Yield strain	5.5	%	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
Izod notched impact strength, +23°C	24	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ISO 1183

Characteristics**Delivery form**

Pellets, Black

Features

Copolymer

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Regional Availability

North America