

**Hostacom TYC 2101N C12507**

PP-T30

LyondellBasell Industries

| <b>Processing/Physical Characteristics</b> | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|--|--------------|-------------|----------------------|
| <b>ISO Data</b>                            |              |             |                      |
| Melt flow index, MFI                       | <b>35</b>    | g/10min     | ISO 1133             |
| Temperature                                | <b>230</b>   | °C          | -                    |
| Load                                       | <b>2.16</b>  | kg          | -                    |

| <b>Mechanical properties</b>          | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|---------------------------------------|--------------|-------------------|----------------------|
| <b>ISO Data</b>                       |              |                   |                      |
| Yield stress                          | <b>16</b>    | MPa               | ISO 527              |
| Flexural modulus, 23°C                | <b>1900</b>  | MPa               | ISO 178              |
| Charpy impact strength, +23°C         | <b>N</b>     | kJ/m <sup>2</sup> | ISO 179/1eU          |
| Charpy notched impact strength, +23°C | <b>10</b>    | kJ/m <sup>2</sup> | ISO 179/1eA          |
| Charpy notched impact strength, -30°C | <b>3</b>     | kJ/m <sup>2</sup> | ISO 179/1eA          |

| <b>Thermal properties</b>                | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|--|--------------|-------------|----------------------|
| <b>ISO Data</b>                          |              |             |                      |
| Temp. of deflection under load, 1.80 MPa | <b>56</b>    | °C          | ISO 75-1/-2          |
| Vicat softening temperature, A           | <b>128</b>   | °C          | ISO 306              |

| <b>Other properties</b> | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|-------------------------|--------------|-------------------|----------------------|
| Density                 | <b>1130</b>  | kg/m <sup>3</sup> | ISO 1183             |

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Features**

Non Blooming, Copolymer

**Applications**

Automotive

**Regional Availability**

Europe