

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	18	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	25	MPa	ISO 527
Strain at break	16	%	ISO 527
Flexural modulus, 23°C	2800	MPa	ISO 178
Charpy impact strength, +23°C	80	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	10	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	61	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	1140	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets

### Features

Copolymer

### Applications

Automotive

### Regional Availability

Europe