

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|---------|-----------------|
| ISO Data | | | |
| Melt flow index, MFI | 14 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 5 | kg | - |
| Molding shrinkage, parallel | 0.9 | % | ISO 294-4, 2577 |

| Mechanical properties | Value | Unit | Test Standard |
|-------------------------------------|-------|-------------------|---------------|
| ISO Data | | | |
| Yield stress | 24 | MPa | ISO 527 |
| Flexural modulus, 23°C | 2300 | MPa | ISO 178 |
| Izod notched impact strength, +23°C | 6 | kJ/m ² | ISO 180/1A |

| Thermal properties | Value | Unit | Test Standard |
|--|-------|-------|-----------------|
| ISO Data | | | |
| Temp. of deflection under load, 1.80 MPa | 64 | °C | ISO 75-1/-2 |
| Vicat softening temperature, B | 60 | °C | ISO 306 |
| Burning behav. at 1.5 mm nom. thickn. | HB | class | IEC 60695-11-10 |
| Thickness tested | 1.6 | mm | - |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 1140 | kg/m ³ | ISO 1183 |

Characteristics

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Copolymer

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America