

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	14	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Yield stress	30	MPa	ISO 527
Flexural modulus, 23°C	3600	MPa	ISO 178
Izod notched impact strength, +23°C	3.8	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	78	°C	ISO 75-1/-2
Vicat softening temperature, B	95	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	1.2	mm	-
Yellow Card available	yes	-	-
Other properties			
Density	1140	kg/m ³	ISO 1183

Characteristics

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America