

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	33	MPa	ISO 527
Flexural modulus, 23°C	3400	MPa	ISO 178
Izod notched impact strength, +23°C	3.3	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Vicat softening temperature, B	100	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	1.2	mm	-
Yellow Card available	yes	-	-
<b>Other properties</b>			
Density	1130	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Features

Homopolymer

### Certifications

RoHS compliant

### Regional Availability

North America, Europe, Asia Pacific, South and Central America