

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	20	MPa	ISO 527
Flexural modulus, 23°C	2300	MPa	ISO 178
Izod notched impact strength, +23°C	9	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Vicat softening temperature, B	57	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Density	1120	kg/m ³	ISO 1183

Characteristics

Special Characteristics

U.V. stabilized or stable to weather

Features

Copolymer

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America