

**Meplen EH T30 V2**

PP-T30

Mepol S.r.l.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	30	MPa	ISO 527
Strain at break	20	%	ISO 527
Flexural modulus, 23°C	3000	MPa	ISO 178
Izod notched impact strength, +23°C	3	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	2.5	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	0	°C	-
Shore D hardness	76	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	72	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	135	°C	ISO 75-1/-2
Vicat softening temperature, A	154	°C	ISO 306
Vicat softening temperature, B	100	°C	ISO 306
Burning behav. at thickness h	V-2	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	1130	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

Anti-static, Flame retardant, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Regional Availability**

Europe

**Features**

Homopolymer