Polimaxx 2564PCX TA6

PP-T30 IRPC

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	**13**	g/10min	ASTM D 1238
Temperature	**230**	°C	-
Load	**2.16**	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	**22.1**	MPa	ASTM D 638
Elongation at Break	**8**	%	ASTM D 638
Flexural Modulus	**3335**	MPa	ASTM D 790
Rockwell Hardness	**R 88**	-	ASTM D 785
Izod Impact notched, 1/8 in	**49**	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	**140**	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	**1140**	kg/m³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**80 - 85**	°C	-
Pre-drying - Time	**2 - 3**	h	-
Melt temperature	**190 - 240**	°C	-

Characteristics

Processing

Injection Molding

Applications

Automotive, Electrical and Electronical

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

Europe, Asia Pacific

Features

Copolymer

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.