

**Polycompound PP C T 230**

PP-T30

A. Westensee und Partner Rohstoff GmbH

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>2.5</b>	g/10min	ISO 1133
Molding shrinkage, parallel	<b>0.9</b>	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>3100</b>	MPa	ISO 527
Yield stress	<b>24</b>	MPa	ISO 527
Strain at break	<b>30</b>	%	ISO 527
Charpy notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1130</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Other Extrusion

**Regional Availability**

Europe