

Polycompound PP H T 230

PP-T30

A. Westensee und Partner Rohstoff GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2.5	g/10min	ISO 1133
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3600	MPa	ISO 527
Yield stress	31	MPa	ISO 527
Strain at break	20	%	ISO 527
Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ISO 1183

Characteristics**Processing**

Other Extrusion

Regional Availability

Europe