

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	37.6	MPa	ASTM D 638
Flexural Modulus	3241	MPa	ASTM D 790
Rockwell Hardness	R99	-	ASTM D 785
Izod Impact notched, 1/8 in	32	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	127	°C	ASTM D 648
DTUL @ 264 psi	73.9	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Features

Copolymer, Impact Copolymer

Special Characteristics

High impact or impact modified

Regional Availability

North America