

SCOLEFIN® 53 T 10

PP-T30

Ravago Group

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	3000	MPa	ISO 178
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Vicat softening temperature, B	100	°C	ISO 306
Other properties			
Density	1150	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	2 - 4	h	-
Mold temperature	30 - 50	°C	-
Zone 1	220 - 260	°C	-

Characteristics**Processing**

Injection Molding

Features

Homopolymer

Delivery form

Natural Color

Regional Availability

Europe