

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|-------|-------------------|-----------------|
| ISO Data | | | |
| Melt flow index, MFI | 10 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Molding shrinkage, parallel | 0.8 | % | ISO 294-4, 2577 |
| Molding shrinkage, normal | 0.8 | % | ISO 294-4, 2577 |
| Mechanical properties | | | |
| ISO Data | | | |
| Tensile Modulus | 1850 | MPa | ISO 527 |
| Tensile Strength | 17 | MPa | ISO 527 |
| Flexural modulus, 23°C | 1950 | MPa | ISO 178 |
| Charpy impact strength, +23°C | N | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, +23°C | 35 | kJ/m ² | ISO 179/1eA |
| Thermal properties | | | |
| ISO Data | | | |
| Temp. of deflection under load, 1.80 MPa | 88 | °C | ISO 75-1/-2 |
| Vicat softening temperature, B | 130 | °C | ISO 306 |
| Other properties | | | |
| Density | 1120 | kg/m ³ | ISO 1183 |

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Special Characteristics

High impact or impact modified

Applications

General Purpose

Regional Availability

Europe