

Hifax TYC 258X S92908

PP-T35

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	18	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus, 23°C	1950	MPa	ISO 178
Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	2.5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Vicat softening temperature, A	110	°C	ISO 306
Other properties			
Density	1140	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Features

Copolymer

Delivery form

Pellets

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe