

FORMPOLY TPP40

PP-T40

Formulated Polymers Limited

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|---------------|-------------|----------------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 10 | g/10min | ASTM D 1238 |
| Mold Shrinkage, MD | 0.0035 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength | 30 | MPa | ASTM D 638 |
| Elongation at Break | 8 | % | ASTM D 638 |
| Flexural Modulus | 4000 | MPa | ASTM D 790 |
| Flexural Strength | 50 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 39.2 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| DTUL @ 66 psi | 140 | °C | ASTM D 648 |
| DTUL @ 264 psi | 90 | °C | ASTM D 648 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1230 | kg/m ³ | ASTM D 792 |

Characteristics**Delivery form**

Pellets

Features

Low Odor

Additives

Lubricants

Applications

Automotive

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Asia Pacific