

Product Texts

Hostacom

M4 N01 102943 is a 40% talc filled PP homopolymer, with low melt flow rate and outstanding stiffness. Product is available as a customized color matched, pellet form. This grade is delivered in 102943 color version.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	11	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	4000	MPa	ISO 527
^[C] Yield stress	32	MPa	ISO 527
^[C] Yield strain	4	%	ISO 527
^[C] Charpy impact strength, +23°C	30	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	2.0	mm	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1210	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Homopolymer

Delivery form

Granules

Regional Availability

Europe