

Hostacom M4 U04 100000

PP-T40

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	12	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	4000	MPa	ISO 527
Yield stress	38	MPa	ISO 527
Charpy impact strength, +23°C	25	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	70	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	125	°C	ISO 75-1/-2
Vicat softening temperature, B	93	°C	ISO 306
Other properties			
Density	1200	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Applications

Automotive

Delivery form

Pellets, Black

Regional Availability

Europe

Features

Homopolymer