

Hostacom T 60 T4 NERO

PP-T40

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	29	MPa	ISO 527
Flexural modulus, 23°C	3500	MPa	ISO 178
Izod notched impact strength, +23°C	2.5	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	1250	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Features

Homopolymer

Delivery form

Black

Applications

Automotive

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe