

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	4000	MPa	ISO 527
Yield stress	31	MPa	ISO 527
Yield strain	3.6	%	ISO 527
Nominal strain at break	7	%	ISO 527
Flexural modulus, 23°C	4100	MPa	ISO 178
Charpy impact strength, +23°C	30	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	13	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	1.6	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	79	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	133	°C	ISO 75-1/-2
Vicat softening temperature, A	156	°C	ISO 306
Vicat softening temperature, B	93	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2	h	-
Processing humidity	≤0.07	%	-
Melt temperature	230 - 250	°C	-
Mold temperature	10 - 50	°C	-
Zone 1	190 - 240	°C	-

Characteristics

Processing

Injection Molding

Features

Thermal Stability, Homopolymer

Delivery form

Natural Color

Regional Availability

Europe