

MAXTEL 600T40 UV

PP-T40

MRC Polymers, Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	17	MPa	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
Izod notched impact strength, +23°C	7	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Other properties			
Density	1260	kg/m ³	ISO 1183

Characteristics**Delivery form**

Black

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America

Features

Copolymer