

Polycompound PP C T 240

PP-T40

A. Westensee und Partner Rohstoff GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2.5	g/10min	ISO 1133
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3700	MPa	ISO 527
Yield stress	26	MPa	ISO 527
Strain at break	5	%	ISO 527
Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ISO 1183

Characteristics**Processing**

Other Extrusion

Regional Availability

Europe