

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	8	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	4200	MPa	ISO 527
^[C] Stress at break	24	MPa	ISO 527
^[C] Strain at break	4.6	%	ISO 527
^[C] Charpy impact strength, +23°C	20	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	11	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	2.5	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	1.8	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	130	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	90	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
^[C] Burning rate, FMVSS, Thickness 1 mm	100	mm/min	ISO 3795 (FMVSS 302)

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1250	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa