

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>32</b>	MPa	ASTM D 638
Flexural Modulus	<b>3310</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R97</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>25</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>134</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>76</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1230</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Injection Molding

**Features**

Homopolymer

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

North America