

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	37.9	MPa	ASTM D 638
Elongation at Break	15	%	ASTM D 638
Flexural Modulus	3551	MPa	ASTM D 790
Flexural Strength	41.6	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	127	°C	ASTM D 648
DTUL @ 264 psi	82.2	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1220	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Features

Homopolymer

#### Regional Availability

North America