

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	22	MPa	ASTM D 638
Elongation at Break	33	%	ASTM D 638
Flexural Modulus	2500	MPa	ASTM D 790
Flexural Strength	37	MPa	ASTM D 790
Izod Impact notched, 1/8 in	72.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	108	°C	ASTM D 648
DTUL @ 264 psi	55	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1200	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Features

Homopolymer

#### Special Characteristics

High impact or impact modified

#### Regional Availability

North America