

Primefin V500TL40

PP-T40

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	6	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.007	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	31	MPa	ASTM D 638
Elongation at Break	10	%	ASTM D 638
Flexural Modulus	3103	MPa	ASTM D 790
Flexural Strength	53.8	MPa	ASTM D 790
Izod Impact notched, 1/8 in	37.4	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 264 psi	79.4	°C	ASTM D 648
Other properties			
Density	1240	kg/m ³	ASTM D 792

Characteristics**Features**

Homopolymer

Regional Availability

North America