

Panlite® AM-9730FZ

(PC+Polyester)

Teijin Chemicals Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	9	cm ³ /10min	ISO 1133
Temperature	280	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	3500	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Yield strain	4	%	ISO 527
Stress at break	50	MPa	ISO 527
Strain at break	100	%	ISO 527
Flexural modulus, 23°C	3300	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	35	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	12	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	105	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	132	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	50	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	70	E-6/K	ISO 11359-1/-2
Electrical properties			
ISO Data			
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Other properties			
Density	1290	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	5 - 8	h	-
Melt temperature	260 - 280	°C	-
Mold temperature	50 - 80	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Chemical Resistance

General Chemical Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa