

Other properties	Value	Unit	Test Standard
Density	1700	kg/m ³	ISO 1183
Bulk density	950	kg/m ³	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	2 - 4	h	-
Mold temperature	30 - 50	°C	-
Zone 1	220 - 260	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Features

Homopolymer