

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>2730</b>	MPa	ISO 527
Yield stress	<b>27.9</b>	MPa	ISO 527
Yield strain	<b>3.57</b>	%	ISO 527
Stress at break	<b>26.7</b>	MPa	ISO 527
Strain at break	<b>4.48</b>	%	ISO 527
Charpy impact strength, +23°C	<b>10.3</b>	kJ/m <sup>2</sup>	ISO 179/1eU

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets

### Features

Low Odor

### Certifications

Contains renewable resources

### Regional Availability

North America, Europe, Asia Pacific, South and Central America