

Fasal BIO 337

PP-W...

FASAL WOOD KEG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3900	MPa	ISO 527
Tensile Strength	32.9	MPa	ISO 527
Flexural modulus, 23°C	3500	MPa	ISO 178
Charpy impact strength, +23°C	9.6	kJ/m ²	ISO 179/1eU

Other properties	Value	Unit	Test Standard
Density	1160	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	130	°C	-
Pre-drying - Time	4	h	-
Mold temperature	20 - 60	°C	-
Feed temperature	170	°C	-
Zone 1	180	°C	-
Zone 2	180	°C	-
Nozzle temperature	190	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Features

Low Odor

Certifications

Contains renewable resources

Regional Availability

Europe