

**S2 60**

PP-W

Werzalit GmbH + Co. KG

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Flexural modulus, 23°C	<b>5850</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>11</b>	kJ/m <sup>2</sup>	ISO 179/1eU

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1100</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Delivery form**

Granules, Brown

**Special Characteristics**

U.V. stabilized or stable to weather

**Certifications**

Contains renewable resources

**Applications**

Automotive, Packaging

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa