Beobase 25/75 PPC injection CG 74

PP-W25 Beologic nv

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	**2620**	MPa	ISO 527
Tensile Strength	**33.2**	MPa	ISO 527
Strain at break	**3.9**	%	ISO 527
Charpy impact strength, +23°C	**16.1**	kJ/m²	ISO 179/1eU

Other properties	Value	Unit	Test Standard
Biobased content	**25**	%	-
Bulk density	**600**	kg/m³	-

Characteristics

Processing

Injection Molding

Features

Copolymer

Certifications

Contains renewable resources

Regional Availability

Europe, Near East/Africa

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.