

Polywood S3 50 PP 10096

PP-W50

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	5610	MPa	ISO 527
Tensile Strength	44	MPa	ISO 527
Strain at break	1.8	%	ISO 527
Flexural modulus, 23°C	4170	MPa	ISO 178
Charpy impact strength, +23°C	13.2	kJ/m ²	ISO 179/1eU
Other properties			
Density	1200	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Certifications

Contains renewable resources

Delivery form

Pellets

Applications

Automotive

Features

Acoustical Barrier Properties

Regional Availability

Europe