

## Polywood P 60 PP 10107

PP-W60

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	13.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	4020	MPa	ISO 527
Tensile Strength	41.6	MPa	ISO 527
Charpy impact strength, +23°C	12.2	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	4.29	kJ/m <sup>2</sup>	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	1140	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Delivery form

Pellets

#### Certifications

Contains renewable resources

#### Applications

Automotive

#### Regional Availability

Europe