

Polywood P 70 PP 10079

PP-W70

Advanced Compounding GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3280	MPa	ISO 527
Tensile Strength	23.8	MPa	ISO 527
Strain at break	4.4	%	ISO 527
Flexural modulus, 23°C	2740	MPa	ISO 178
Charpy impact strength, +23°C	16.2	kJ/m ²	ISO 179/1eU

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Brown

Special Characteristics

High impact or impact modified

Certifications

Contains renewable resources

Applications

Automotive

Regional Availability

Europe