

Polywood S3 70 PP48 A1

PP-W70

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6800	MPa	ISO 527
Tensile Strength	57.2	MPa	ISO 527
Strain at break	1.7	%	ISO 527
Flexural modulus, 23°C	6900	MPa	ISO 178
Charpy impact strength, +23°C	15.3	kJ/m ²	ISO 179/1eU
Other properties			
Density	1210	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Applications

Automotive

Delivery form

Pellets

Regional Availability

Europe

Certifications

Contains renewable resources