

Polywood S3 75 PP7 A2 13

PP-W75

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3600	MPa	ISO 527
Tensile Strength	32	MPa	ISO 527
Strain at break	4.1	%	ISO 527
Flexural modulus, 23°C	3850	MPa	ISO 178
Charpy impact strength, +23°C	16.5	kJ/m ²	ISO 179/1eU

Characteristics

Processing

Injection Molding

Certifications

Contains renewable resources

Delivery form

Pellets

Applications

Automotive

Special Characteristics

High impact or impact modified

Regional Availability

Europe