

Product Texts

Base Polymer	Polypropylene Homopolymer
Filler/Additive System	8 % special filler,30 % mineral
Special Features	highly reflective,opaque
Market Segment	Automotive,Lighting
Application Area	lighting,light blocking components
Typical Applications	light guides,reflectors

Processing/Physical Characteristics

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Melt volume-flow rate, MVR	25	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Tensile Modulus	3900	MPa	ISO 527
^[C] Yield stress	31	MPa	ISO 527
^[C] Yield strain	2.8	%	ISO 527
^[C] Charpy impact strength, +23°C	23	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	2	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Temp. of deflection under load, 1.80 MPa	86	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	100	°C	ISO 306

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
--	-------	------	---------------

^[C] Density	1220	kg/m ³	ISO 1183
------------------------	------	-------------------	----------

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Light Blocking

Delivery form

White

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-100 °C for 2-3 h in an air circulating dryer 80-100 °C for 2-4 h max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 230-270 °C mould temperature 20-90 °C
Storage	dry, protected from light