

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>1.8</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
Melt flow index, MFI	<b>1.45</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Other properties</b>			
Density	<b>940</b>	kg/m <sup>3</sup>	ISO 1183
Bulk density	<b>570</b>	kg/m <sup>3</sup>	-

### Characteristics

#### Delivery form

Pellets, Black

#### Regional Availability

Europe

#### Certifications

Recycled Resin Content