

Product Texts

RF material

Property	Value
Dielectric constant, 2.4 GHz	2.61
Tolerance	±0.05
Loss tangent, 2.4 GHz	0.0012

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	300	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	42	MPa	ISO 527
Yield stress	68	MPa	ISO 527
Yield strain	6	%	ISO 527
Strain at break	20	%	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	14	kJ/m ²	ISO 180/1A
Izod notched impact strength	12	kJ/m ²	ISO 180/1A
Temperature	-20	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	148	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	176	°C	ISO 75-1/-2
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Other properties	Value	Unit	Test Standard
Water absorption	0.25	%	Sim. to ISO 62
Density	1080	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Europe, Asia Pacific