

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>8</b>	g/10min	ASTM D 1238
Temperature	<b>280</b>	°C	-
Load	<b>5</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Modulus	<b>981</b>	MPa	ASTM D 638
Tensile Strength	<b>44.1</b>	MPa	ASTM D 638
Elongation at Break	<b>60</b>	%	ASTM D 638
Flexural Modulus	<b>1766</b>	MPa	ASTM D 790
Flexural Strength	<b>68.7</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>235</b>	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	<b>98.1</b>	J/m	ASTM D 256
Temperature	<b>-30</b>	°C	-
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>186</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>1060</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat

**Regional Availability**

Europe, Asia Pacific

**Chemical Resistance**

General Chemical Resistance