

| <b>Mechanical properties</b>          | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|---------------------------------------|--------------|-------------------|----------------------|
| <b>ISO Data</b>                       |              |                   |                      |
| Tensile Strength                      | <b>73</b>    | MPa               | ISO 527              |
| Flexural modulus, 23°C                | <b>3900</b>  | MPa               | ISO 178              |
| Flexural strength                     | <b>105</b>   | MPa               | ISO 178              |
| Charpy notched impact strength, +23°C | <b>4</b>     | kJ/m <sup>2</sup> | ISO 179/1eA          |

| <b>Thermal properties</b>                   | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|---|--------------|-------------|----------------------|
| <b>ISO Data</b>                             |              |             |                      |
| Temp. of deflection under load, 1.80 MPa    | <b>97</b>    | °C          | ISO 75-1/-2          |
| Coeff. of linear therm. expansion, parallel | <b>60</b>    | E-6/K       | ISO 11359-1/-2       |
| Burning behav. at 1.5 mm nom. thickn.       | <b>V-0</b>   | class       | IEC 60695-11-10      |
| Thickness tested                            | <b>1.6</b>   | mm          | -                    |
| Burning behav. 5V at thickness h            | <b>5VA</b>   | class       | IEC 60695-11-20      |
| Thickness tested                            | <b>2.5</b>   | mm          | -                    |
| <b>ASTM Data</b>                            |              |             |                      |
| DTUL @ 264 psi                              | <b>100</b>   | °C          | ASTM D 648           |

| <b>Electrical properties</b> | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|------------------------------|--------------|-------------|----------------------|
| <b>ISO Data</b>              |              |             |                      |
| Relative permittivity, 100Hz | <b>3.1</b>   | -           | IEC 62631-2-1        |
| Relative permittivity, 1MHz  | <b>3</b>     | -           | IEC 62631-2-1        |
| Dissipation factor, 100Hz    | <b>30</b>    | E-4         | IEC 62631-2-1        |
| Dissipation factor, 1MHz     | <b>60</b>    | E-4         | IEC 62631-2-1        |
| Volume resistivity           | <b>1E14</b>  | Ohm*m       | IEC 62631-3-1        |
| Surface resistivity          | <b>1E16</b>  | Ohm         | IEC 62631-3-2        |

| <b>Other properties</b> | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|-------------------------|--------------|-------------------|----------------------|
| Density                 | <b>1150</b>  | kg/m <sup>3</sup> | ISO 1183             |

| <b>Processing Recommendation Injection Molding</b> | <b>Value</b>     | <b>Unit</b> | <b>Test Standard</b> |
|--|------------------|-------------|----------------------|
| Pre-drying - Temperature                           | <b>90 - 100</b>  | °C          | -                    |
| Pre-drying - Time                                  | <b>2 - 4</b>     | h           | -                    |
| Melt temperature                                   | <b>240 - 280</b> | °C          | -                    |
| Mold temperature                                   | <b>60 - 90</b>   | °C          | -                    |

**Characteristics**

**Processing**

Injection Molding

**Features**

Low Warpage

**Regional Availability**

North America, Europe, Asia Pacific