

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.0025	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	64.7	MPa	ASTM D 638
Elongation at Break	25	%	ASTM D 638
Flexural Modulus	2207	MPa	ASTM D 790
Flexural Strength	103	MPa	ASTM D 790
Rockwell Hardness	L 105	-	ASTM D 785
Izod Impact notched, 1/8 in	98.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 264 psi	168	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1050	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Special Characteristics

Heat stabilized or stable to heat

### Features

Low Warpage

### Applications

Electrical and Electronical

### Regional Availability

Asia Pacific