

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0016</b>	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>110</b>	MPa	ASTM D 638
Flexural Modulus	<b>9810</b>	MPa	ASTM D 790
Flexural Strength	<b>147</b>	MPa	ASTM D 790
Rockwell Hardness	<b>L 100</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>49.1</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>170</b>	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Surface Resistivity	<b>1000000</b>	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	<b>1230</b>	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Delivery form

Black

### Special Characteristics

Heat stabilized or stable to heat

### Features

Low Warpage

### Applications

Electrical and Electronical

### Regional Availability

Asia Pacific