

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Stress at break	90	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	4500	MPa	ISO 178
Flexural strength	110	MPa	ISO 178
Charpy notched impact strength, +23°C	3	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	3	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	130	°C	ISO 75-1/-2
Vicat softening temperature, B	135	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Other properties	Value	Unit	Test Standard
Density	1210	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	280 - 310	°C	-
Mold temperature	80 - 100	°C	-

## Characteristics

### Processing

Injection Molding

### Certifications

Drinking water contact, RoHS compliant

### Applications

Electrical and Electronical

### Regional Availability

North America, Europe, Asia Pacific, South and Central America